



Telcar® TL-1445U

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-1445U is a general purpose thermoplastic elastomer designed for the industrial market. Telcar TL-1445U is UV stable and is suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Filled • Good Colorability • Good Mold Release • Good Moldability	• Good Processability • Good Processing Stability • Light Stabilized • Low Density • Low Flow	• Low Specific Gravity • Medium Hardness • Slip
Uses	• General Purpose	• Impregnation Applications	• Weatherstripping
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.980		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	3.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	362	psi	
Flow : 100% Strain	644	psi	
Tensile Stress - Across Flow ² (300% Strain)	550	psi	ASTM D412
Tensile Strength ²			ASTM D412
Across Flow : Break	1660	psi	
Flow : Break	747	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	690	%	
Flow : Break	240	%	
Tear Strength ²			ASTM D624
Across Flow	224	lbf/in	
Flow	170	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	20	%	
158°F, 22 hr	41	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	66		
Shore A, 5 sec, Injection Molded	64		

Telcar® TL-1445U

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	420 to 460	°F
Middle Temperature	420 to 460	°F
Front Temperature	420 to 460	°F
Nozzle Temperature	420 to 460	°F
Processing (Melt) Temp	420 to 460	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	400 to 440	°F
Cylinder Zone 2 Temp.	400 to 440	°F
Cylinder Zone 3 Temp.	400 to 440	°F
Cylinder Zone 4 Temp.	400 to 440	°F
Cylinder Zone 5 Temp.	400 to 440	°F
Die Temperature	400 to 440	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1