



Telcar® TL-2530A

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-2530A is a general purpose, low density thermoplastic elastomer designed for injection molding applications.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • General Purpose • Good Colorability • Good Mold Release	• Good Moldability • Good Processability • High Flow • Low Density	• Low Hardness • Low Specific Gravity
Uses	• General Purpose • Grommets	• Industrial Applications • Industrial Parts	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Translucent
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	700	psi	ASTM D412
Tensile Elongation (Break)	800	%	ASTM D412
Tear Strength			ASTM D624
Across Flow	75.0	lbf/in	
Flow	66.0	lbf/in	
Compression Set			ASTM D395
73°F, 22 hr	12	%	
158°F, 22 hr	28	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	34		ASTM D2240

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F

Telcar® TL-2530A
Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Notes

¹ Typical properties: these are not to be construed as specifications.