



Telcar® TL-2363T

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-2363T is a UV resistant thermoplastic elastomer designed for outdoor applications requiring a soft, rubber-like feel. Telcar TL-2363T is a high hardness grade that exhibits excellent abrasion resistance, suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Ablation Resistant • Brominated • Filled • Flame Retardant • Good Color Stability • Good Colorability	• Good Flow • Good Gloss • Good Mold Release • Good Moldability • Good Processability • Good Processing Stability	• High Flow • High Hardness • Light Stabilized • Lubricated • Medium Density • Slip
Uses	• Consumer Applications	• Flooring	
RoHS Compliance	• RoHS Compliant		
Appearance	• Blue • Colors Available	• Natural Color • Opaque	
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.02		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	878	psi	
Flow : 100% Strain	1180	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	1060	psi	
Flow : 300% Strain	1380	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	1430	psi	
Flow : Break	1810	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	520	%	
Flow : Break	550	%	
Tear Strength ²			ASTM D624
Across Flow	267	lbf/in	
Flow	329	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	44	%	
158°F, 22 hr	85	%	

Telcar® TL-2363T

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	90		
Shore A, 5 sec, Injection Molded	88		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	20	%	ASTM D2863

Processing Information			
Injection	Nominal Value	Unit	
Rear Temperature	340 to 380	°F	
Middle Temperature	350 to 390	°F	
Front Temperature	360 to 400	°F	
Nozzle Temperature	370 to 410	°F	
Processing (Melt) Temp	370 to 410	°F	
Mold Temperature	77 to 150	°F	
Injection Pressure	200 to 1000	psi	
Injection Rate	Moderate-Fast		
Back Pressure	25.0 to 50.0	psi	
Screw Speed	50 to 100	rpm	
Cushion	0.150 to 1.00	in	
Injection Notes			
Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).			

Notes

- ¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1