



Telcar® TL-2417J NAT

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-2417J NAT is a high performance thermoplastic elastomer, available in NAT, designed for a variety of consumer and industrial applications. Telcar TL-2417J NAT is a high density, high hardness, flame retardant grade suitable for extrusion and extrusion coating.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Flame Retardant • Good Adhesion • Good Colorability	• Good Flow • Good Processability • Good Surface Finish • Good Toughness	• High Density • High Hardness • High Specific Gravity
Uses	• Consumer Applications	• Fabric Coatings	• Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Extrusion Coating	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.07		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	743	psi	
Flow : 100% Strain	925	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	697	psi	
Flow : 300% Strain	963	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	774	psi	
Flow : Break	969	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	480	%	
Flow : Break	380	%	
Tear Strength ²			ASTM D624
Across Flow	320	lbf/in	
Flow	385	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	46	%	
158°F, 22 hr	85	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	89		
Shore A, 5 sec, Injection Molded	87		

Telcar® TL-2417J NAT

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	360 to 400	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1