



Telcar® TL-2540F

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-2540F is a general purpose thermoplastic elastomer designed for a variety of industrial applications. Telcar TL-2540F is a high density, medium hardness grade suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Filled • General Purpose • Good Colorability	• Good Mold Release • Good Moldability • Good Processability • High Density	• High Flow • High Specific Gravity • Medium Hardness
Uses	• General Purpose • Grommets	• Industrial Applications • Industrial Parts	• Rubber Replacement
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.18		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.1	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	650	psi	ASTM D412
Tensile Elongation (Break)	800	%	ASTM D412
Tear Strength			ASTM D624
Across Flow	99.0	lbf/in	
Flow	91.0	lbf/in	
Compression Set			ASTM D395
73°F, 22 hr	17	%	
158°F, 22 hr	41	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec	47		
Shore A, 15 sec	42		
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 207 sec ⁻¹)	134	Pa·s	ASTM D3835

Telcar® TL-2540F

Teknor Apex Company - Thermoplastic Elastomer

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Notes

¹ Typical properties: these are not to be construed as specifications.