



Telcar® TL-8451 BLK 940

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-8451 BLK 940 is a high performance, halogen-free thermoplastic elastomer designed for electrical applications requiring flexibility over a wide temperature range. Telcar TL-8451 BLK 940 is a high durometer grade that is UV stablized and RoHS compliant. This grade is UL listed and is suitable for both injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose • Good Colorability • Good Flexibility • Halogen Free • Heat Aging Resistant	• High Elasticity • High Elongation • High Tensile Strength • Medium Flow • Ozone Resistant	• Sunlight Resistant (720 hours) • UV Resistant • Weather Resistant
Uses	• Appliance Wire Insulation • Appliance Wire Jacketing • Cable Jacketing • Connectors	• Flexible Cord Jacketing • Industrial Cable Insulation • Terminal Cable Jacketing • Underground Power Cable	• Wire & Cable Applications • Wire Jacketing
Wire Types	• SJEOW		
Agency Ratings	• UL 1581 ¹		
RoHS Compliance	• RoHS Compliant		
UL File Number	• QMTT2.E73402		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ²

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	19	g/10 min	ASTM D1238
Carbon Black Content	2.5	%	ASTM D1603
Mechanical	Nominal Value	Unit	Test Method
Deformation Under Load ³ (302°F)	6.00	%	ASTM D621
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2400	psi	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	82		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	UL 1581
Brittleness Temperature	< -76.0	°F	ASTM D746
RTI Elec	194	°F	UL 746
RTI Str	194	°F	UL 746
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (277°F, 168 hr)	110	%	ASTM D573
Change in Ultimate Elongation in Air (277°F, 168 hr)	89	%	ASTM D573
Change in Tensile Strength 140°F, 168 hr, in IRM 902 Oil	86	%	ASTM D471

Telcar® TL-8451 BLK 940

Teknor Apex Company - Thermoplastic Elastomer

Aging	Nominal Value	Unit	Test Method
Change in Ultimate Elongation 140°F, 168 hr, in IRM 902 Oil	93	%	ASTM D471
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	970	V/mil	ASTM D149
Dielectric Constant			ASTM D150
1 kHz	2.10		
1 MHz	2.33		
Dissipation Factor			ASTM D150
1 kHz	2.0E-4		
1 MHz	1.0E-4		
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.03 in, All Colors)	HB		UL 94
Oxygen Index	18	%	ASTM D2863
Additional Information			
Maximum Continuous Operating Temperature, UL-1581: 105°C			

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	390 to 420	°F
Middle Temperature	415 to 430	°F
Front Temperature	430 to 440	°F
Nozzle Temperature	430 to 445	°F
Processing (Melt) Temp	430 to 445	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C)

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	380 to 410	°F
Cylinder Zone 2 Temp.	390 to 420	°F
Cylinder Zone 3 Temp.	415 to 430	°F
Cylinder Zone 5 Temp.	430 to 440	°F
Die Temperature	430 to 445	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ 105°C

² Typical properties: these are not to be construed as specifications.

³ 2000g weight