



Telcar® TL-81-D954-D

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-81-D954-D is a general purpose thermoplastic elastomer designed for a variety of construction and industrial applications. Telcar TL-81-D954-D is a high density, medium hardness, RoHS compliant, UV stable grade suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Filled • Good Colorability • Good Mold Release • Good Moldability • Good Processability	• Good Processability • Good Toughness • Good Weather Resistance • High Density • High Flow • High Specific Gravity	• Light Stabilized • Low Flow • Lubricated • Medium Hardness • Slip
Uses	• General Purpose • Industrial Applications	• Outdoor Applications • Rubber Replacement	• Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.17		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	16	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	336	psi	
Flow : 100% Strain	473	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	495	psi	
Flow : 300% Strain	620	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	1300	psi	
Flow : Break	925	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	670	%	
Flow : Break	580	%	
Tear Strength ²			ASTM D624
Across Flow	179	lbf/in	
Flow	182	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	30	%	
158°F, 22 hr	58	%	

Telcar® TL-81-D954-D

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	72		
Shore A, 5 sec, Injection Molded	70		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	356 to 396	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1