



Telcar® TL-8730HF NAT XRD3 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-8730HF NAT XRD3 is a high performance, halogen free flame retardant thermoplastic elastomer designed for electrical applications requiring flexibility over a wide temperature range. Telcar TL-8730HF NAT XRD3 is a high durometer grade that is UV stabilized. This grade is suitable for both injection molding and extrusion.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant • General Purpose • Good Colorability • Good Flexibility	• Good Weather Resistance • High Density • High Elasticity • High Hardness	• High Specific Gravity • Medium Flow • Ozone Resistant • UV Resistant
Uses	• Cable Jacketing • Electrical Parts • Electrical/Electronic Applications	• General Purpose • Insulation • Rubber Replacement	• Wire & Cable Applications • Wire Jacketing
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.30		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.6	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	798	psi	ASTM D412
Tensile Stress (300% Strain)	914	psi	ASTM D412
Tensile Strength (Break)	1020	psi	ASTM D412
Tensile Elongation (Break)	400	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	92		ASTM D2240
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	23	%	ASTM D2863

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F

Telcar® TL-8730HF NAT XRD3 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	350 to 390	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F
Extrusion Notes		
Screw Speed: 30 to 100 rpm		

Notes

¹ Typical properties: these are not to be construed as specifications.