



Telcar® TL-8431

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-8431 is a general purpose thermoplastic elastomer designed for electrical applications requiring flexibility over a wide temperature range. Telcar TL-8431 is a medium durometer grade that is UV stabilized. This grade is UL listed and is suitable for both injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose • Good Colorability • Good Flexibility • Good Weather Resistance • Halogen Free	• High Elasticity • High Elongation • High Tensile Strength • Low Flow • Low Temperature Flexibility	• Low Temperature Toughness • Ozone Resistant • Sunlight Resistant (720 hours) • UV Resistant
Uses	• Appliance Wire Insulation • Appliance Wire Jacketing • Cable Jacketing • Connectors	• Electrical/Electronic Applications • Flexible Cord Jacketing • Industrial Cable Insulation • Terminal Cable Jacketing	• Underground Power Cable • Wire & Cable Applications • Wire Jacketing
Wire Types	• SJEOW		
Agency Ratings	• UL 1581 ¹	• UL 94 HB ²	• UL QMTT2
UL File Number	• QMTT2.E73402		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ³

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.922		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	6.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ^{4, 5} (100% Strain, 0.0200 in)	375	psi	ASTM D412
Tensile Stress ^{4, 5} (300% Strain, 0.0200 in)	650	psi	ASTM D412
Tensile Strength ^{4, 5} (Break, 0.0200 in)	2550	psi	ASTM D412
Tensile Elongation ^{4, 5} (Break, 0.0200 in)	700	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	69		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	UL 1581
Brittleness Temperature	-148	°F	ASTM D746
RTI Elec	194	°F	UL 746B
RTI Str	194	°F	UL 746B
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (277°F, 168 hr)	6.0	%	ASTM D573
Change in Ultimate Elongation in Air (277°F, 168 hr)	-6.0	%	ASTM D573
Change in Tensile Strength 140°F, 168 hr, in IRM 902 Oil	-20	%	ASTM D471
Change in Ultimate Elongation 140°F, 168 hr, in IRM 902 Oil	-10	%	ASTM D471

Telcar® TL-8431

Teknor Apex Company - Thermoplastic Elastomer

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (122°F)	9.1E+16	ohms·cm	ASTM D257
Dielectric Strength	970	V/mil	ASTM D149
Dielectric Constant (1 kHz)	2.10		ASTM D150
Insulation Resistance	1.0E+12	ohms	IEC 60167
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.03 in, All Colors)	HB		UL 94
Oxygen Index	18	%	ASTM D2863
Additional Information			
UL 1581: 720 Hour Sunlight Resistant			

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	390 to 420	°F
Middle Temperature	415 to 430	°F
Front Temperature	430 to 440	°F
Nozzle Temperature	430 to 445	°F
Processing (Melt) Temp	430 to 445	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Injection Notes		
Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C)		
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	380 to 410	°F
Cylinder Zone 2 Temp.	390 to 420	°F
Cylinder Zone 3 Temp.	415 to 430	°F
Cylinder Zone 4 Temp.	415 to 430	°F
Cylinder Zone 5 Temp.	430 to 440	°F
Die Temperature	430 to 445	°F
Extrusion Notes		
Screw Speed: 30 to 100 rpm		

Notes

¹ 105°C

² minimum 1.5 mm thickness

³ Typical properties: these are not to be construed as specifications.

⁴ Die C, 20 in/min

⁵ die cut from extruded tapes