



Telcar® TL-8732R

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-8732R is a high performance, flame retardant thermoplastic elastomer designed for electrical applications requiring flexibility over a wide temperature range. Telcar TL-8732R is a medium durometer grade that is UV stabilized. This grade is UL listed and is suitable for both injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant • General Purpose • Good Colorability • Good Flexibility • Good Weather Resistance • Halogenated	• Heat Aging Resistant • High Density • High Elasticity • High Elongation • High Specific Gravity • High Tensile Strength	• Medium Flow • Medium Hardness • Ozone Resistant • Sunlight Resistant (720 hours) • UV Resistant
Uses	• General Purpose	• Rubber Replacement	
Agency Ratings	• UL 1581		
UL File Number	• QMTT2.E73409		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.17		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	10	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ^{2, 3} (100% Strain, 0.0200 in)	470	psi	ASTM D412
Tensile Stress ^{2, 3} (300% Strain, 0.0200 in)	690	psi	ASTM D412
Tensile Strength ^{2, 3} (Break, 0.0200 in)	1700	psi	ASTM D412
Tensile Elongation ^{2, 3} (Break, 0.0200 in)	600	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	80		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	UL 1581
Brittleness Temperature	< -76.0	°F	ASTM D746
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (277°F, 168 hr)	-10	%	ASTM D573
Change in Ultimate Elongation in Air (277°F, 168 hr)	-7.0	%	ASTM D573
Change in Tensile Strength 140°F, 168 hr, in IRM 902 Oil	-4.0	%	ASTM D471
Change in Ultimate Elongation 140°F, 168 hr, in IRM 902 Oil	2.0	%	ASTM D471

Telcar® TL-8732R

Teknor Apex Company - Thermoplastic Elastomer

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity			ASTM D257
73°F	1.4E+16	ohms·cm	
122°F	6.5E+14	ohms·cm	
Dielectric Strength	640	V/mil	ASTM D149
Dielectric Constant (1 kHz)	2.30		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.12 in, All Colors)	V-2		UL 94
Oxygen Index	23	%	ASTM D2863
Additional Information			
Maximum Continuous Operating Temp, UL-1581: 105°C			

Processing Information			
Injection	Nominal Value	Unit	
Rear Temperature	340 to 380	°F	
Middle Temperature	350 to 390	°F	
Front Temperature	360 to 400	°F	
Nozzle Temperature	370 to 410	°F	
Processing (Melt) Temp	370 to 410	°F	
Mold Temperature	77 to 150	°F	
Injection Pressure	200 to 1000	psi	
Injection Rate	Moderate-Fast		
Back Pressure	25.0 to 50.0	psi	
Screw Speed	50 to 100	rpm	
Cushion	0.150 to 1.00	in	
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	330 to 370	°F	
Cylinder Zone 2 Temp.	340 to 380	°F	
Cylinder Zone 3 Temp.	350 to 390	°F	
Cylinder Zone 4 Temp.	350 to 390	°F	
Cylinder Zone 5 Temp.	360 to 400	°F	
Die Temperature	374 to 410	°F	
Extrusion Notes			
Screw Speed: 30 to 100 rpm			

Notes

- ¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ die cut from extruded tapes