



Telcar® TL-2934T

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-2934T is a high performance V-0 flame retardant thermoplastic elastomer designed for electrical applications requiring flexibility over a wide temperature range. Telcar TL-2934T is a high hardness, high density, low flow grade that is UV stabilized and RoHS compliant. This grade is easily colorable and is suitable for both injection molding and extrusion

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Brominated • Filled • Flame Retardant • Good Colorability	• Good Electrical Properties • Halogenated • High Density • High Hardness	• High Specific Gravity • Low Flow • Sunlight Resistant • UV Resistant
Uses	• Cable Jacketing • Electrical/Electronic Applications	• Flame Retardant Insulation • Industrial Applications	• Ribbons
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.30		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2200	psi	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	40		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-58.0	°F	ASTM D746
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (316°F, 168 hr)	-11	%	ASTM D573
Change in Ultimate Elongation in Air (316°F, 168 hr)	-33	%	ASTM D573
Change in Tensile Strength 140°F, 168 hr, in IRM 902 Oil	-8.0	%	ASTM D471
Change in Ultimate Elongation 140°F, 168 hr, in IRM 902 Oil	-6.0	%	ASTM D471
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant (1 kHz)	2.50		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.12 in, NC)	V-0		UL 94
Oxygen Index	28	%	ASTM D2863

Telcar® TL-2934T

Teknor Apex Company - Thermoplastic Elastomer

Processing Information		
Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	350 to 390	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F
Extrusion Notes		
Screw Speed: 30 to 100 rpm		

Notes

¹ Typical properties: these are not to be construed as specifications.