



Medalist® MD-23133 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Vulcanizate

General Information

Product Description

Medalist MD-23133 is a high performance thermoplastic vulcanizate specifically designed for healthcare and medical applications. Medalist MD-23133 is a low hardness, low density, sterilizable grade suitable for injection molding.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Autoclave Sterilizable • Chemical Resistant • Ethylene Oxide Sterilizable • Good Adhesion • Good Processability	• Good Sterilizability • Good Tear Strength • Halogen Free • Low Compression Set • Low Density	• Low Hardness • Low Specific Gravity • Radiation Sterilizable
Uses	• Dental Applications • Gaskets • Hospital Goods	• Medical Devices • Medical/Healthcare Applications • Pharmaceuticals	• Rubber Replacement
Agency Ratings	• ISO 10993-5	• ISO 13485	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	• Opaque
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.910		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	15	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ² (100% Strain)	159	psi	ASTM D412
Tensile Stress ² (300% Strain)	365	psi	ASTM D412
Tensile Strength ² (Break)	410	psi	ASTM D412
Tensile Elongation ² (Break)	350	%	ASTM D412
Tear Strength ²	82.0	lbf/in	ASTM D624
Compression Set ³			ASTM D395B
73°F, 22 hr	13	%	
158°F, 22 hr	25	%	
212°F, 22 hr	44	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	35		
Shore A, 5 sec, Injection Molded	33		

Medalist® MD-23133 (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Vulcanizate

Processing Information		
Injection	Nominal Value	Unit
Rear Temperature	300 to 340	°F
Middle Temperature	340 to 380	°F
Front Temperature	380 to 420	°F
Nozzle Temperature	380 to 420	°F
Processing (Melt) Temp	380 to 420	°F
Mold Temperature	70 to 100	°F
Back Pressure	25.0 to 100	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Injection Notes		

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1