



Sarlink® TPV 2939D

Teknor Apex Company - Thermoplastic Vulcanizate

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Expansion Joint • Gaskets • Glazing	• Grommets • Plugs • Shock Absorbing Pads	• Tubing • Weatherstripping
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.910		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	1900	psi	ASTM D412
Tensile Elongation (Break)	530	%	ASTM D412
Compression Set			ASTM D395
73°F, 22 hr	40	%	
158°F, 22 hr	50	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D, 1 sec	41		
Shore D, 5 sec	39		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	344 to 416	°F
Middle Temperature	354 to 426	°F
Front Temperature	364 to 436	°F
Nozzle Temperature	374 to 446	°F
Processing (Melt) Temp	374 to 446	°F
Mold Temperature	95 to 140	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Fast	
Back Pressure	25.0 to 125	psi
Screw Speed	50 to 120	rpm
Cushion	0.150 to 1.00	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 400	°F
Cylinder Zone 2 Temp.	340 to 410	°F
Cylinder Zone 3 Temp.	350 to 420	°F
Cylinder Zone 5 Temp.	360 to 430	°F
Die Temperature	374 to 440	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm