



Sarlink® TPV 4750B42

Teknor Apex Company - Thermoplastic Vulcanizate

General Information

Product Description

The Sarlink TPV 4700 Series are very high flow injection molding engineering grades with excellent UV resistance, elasticity, and surface aesthetics designed for demanding automotive applications including window encapsulation and exterior parts. Sarlink® TPV 4750B42 is a black, medium hardness, low density thermoplastic vulcanizate suited for injection molding applications that require superior flow properties.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Additive	• UV Stabilizer		
Features	• Chemical Resistant • Good Processability • High Flow • High Heat Resistance	• Low Compression Set • Low Density • Low Specific Gravity • Medium Hardness	• Resilient • UV Resistant
Uses	• Automotive Applications • Automotive Exterior Parts	• Automotive Window Encapsulation • Rubber Replacement	
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• GM GMP.E/P.078 Color: Natural • GM GMW15812P-TPV(EPDM +PP) Type 4M Color: Natural	• GM Sarlink Color • STELLANTIS MS-AR-100 AMV Color: Natural	
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.910		ASTM D792
Density	0.910	g/cm³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Across Flow : 100% Strain	218	psi	
Flow : 100% Strain	319	psi	
Tensile Stress			ISO 37
Across Flow : 100% Strain	218	psi	
Flow : 100% Strain	319	psi	
Tensile Strength			ASTM D412
Across Flow : Break	609	psi	
Flow : Break	566	psi	
Tensile Stress			ISO 37
Across Flow : Break	609	psi	
Flow : Break	566	psi	
Tensile Elongation			ASTM D412
Across Flow : Break	440	%	
Flow : Break	320	%	
Tensile Elongation			ISO 37
Across Flow : Break	440	%	
Flow : Break	320	%	

Sarlink® TPV 4750B42

Teknor Apex Company - Thermoplastic Vulcanizate

Elastomers	Nominal Value	Unit	Test Method
Tear Strength - Across Flow	91.0	lbf/in	ASTM D624
Tear Strength - Across Flow ²	91.4	lbf/in	ISO 34-1
Compression Set			ASTM D395
73°F, 22 hr	15	%	
158°F, 22 hr	26	%	
257°F, 70 hr	40	%	
Compression Set			ISO 815
73°F, 22 hr	15	%	
158°F, 22 hr	26	%	
257°F, 70 hr	40	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	50		
Shore A, 5 sec, Injection Molded	53		
Shore Hardness			ISO 868
Shore A, 5 sec, Extruded	50		
Shore A, 5 sec, Injection Molded	53		
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			ASTM D573
275°F, 1000 hr	-11	%	
100% Strain, 275°F, 1000 hr	-1.0	%	
302°F, 168 hr	-20	%	
100% Strain, 302°F, 168 hr	-7.0	%	
Change in Tensile Strength in Air - Across Flow			ISO 188
275°F, 1000 hr	-11	%	
100% Strain 275°F, 1000 hr	-1.0	%	
302°F, 168 hr	-20	%	
100% Strain 302°F, 168 hr	-7.0	%	
Change in Ultimate Elongation in Air - Across Flow			ASTM D573
275°F, 1000 hr	-1.0	%	
302°F, 168 hr	-13	%	
Change in Tensile Strain at Break in Air - Across Flow			ISO 188
275°F, 1000 hr	-1.0	%	
302°F, 168 hr	-13	%	
Change in Durometer Hardness in Air			ASTM D573
Shore A, 275°F, 1000 hr	2.0		
Shore A, 302°F, 168 hr	-1.0		
Change in Shore Hardness in Air			ISO 188
Shore A, 275°F, 1000 hr	2.0		
Shore A, 302°F, 168 hr	-1.0		
Change in Volume (257°F, 70 hr, in IRM 903 Oil)	85	%	ASTM D471
Change in Volume (257°F, 70 hr, in IRM 903 Oil)	85	%	ISO 1817
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
392°F	220	Pa·s	ASTM D3835
392°F	220	Pa·s	ISO 11443

Sarlink® TPV 4750B42

Teknor Apex Company - Thermoplastic Vulcanizate

Processing Information		
Injection	Nominal Value	Unit
Drying Temperature - Desiccant Dryer	180	°F
Drying Time - Desiccant Dryer	3.0 to 4.0	hr
Dew Point - Desiccant Dryer	-40	°F
Suggested Shot Size	25 to 50	%
Rear Temperature	356 to 410	°F
Middle Temperature	374 to 428	°F
Front Temperature	392 to 464	°F
Nozzle Temperature	410 to 464	°F
Processing (Melt) Temp	410 to 464	°F
Mold Temperature	50 to 150	°F
Back Pressure	10.0 to 150	psi
Screw Speed	100 to 200	rpm
Screw L/D Ratio	20.0:1.0	

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)