

Technical Data Sheet

 **Alcolor[®]**

MOCOM

ALCOLOR ABS A GN5032-15

Base Polymer	Styrene/Acrylonitrile/Copolymer
Colour	green, similar to RAL 6037
Thermal Stability Colourant	270 °C max.
Light Fastness Colourant	blue woolscale 7
For use in	Acrylonitrile/Butadiene/Styrene/Copolymer
Special Features	free from cadmium, lead and diarylide pigments, dust-free, high dispersibility, high additive content
Market Segment	electrical and electronic, Furniture, building and construction, sport and leisure
Application Area	extruded parts, injection moulded parts, compounding

Dosage	2,0 % extrusion 2,0 % injection moulding dependant on wall thickness and required colour intensity dependant on application and operational area
--------	---

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 3-6 h max. moisture content <0,10 %
-----------------------	---

Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
-------------------------------	---

Storage	dry, protected from light tightly sealed
---------	---