

Technical Data Sheet



ALCOM AWL 15/1 WT1471-04LB

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Filler/Additive System	15 % special filler
Special Features	highly reflective, opaque
Market Segment	Automotive, various
Application Area	lighting, light blocking components
Typical Applications	light guides, reflectors

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 4-8 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2900	MPa	ISO 178
Flexural Stress (3.5% Strain)	71	MPa	ISO 178
Tensile Modulus	2600	MPa	ISO 527
Tensile Stress at Yield	44	MPa	ISO 527
Tensile Elongation at Yield	2.4	%	ISO 527
Tensile Elongation at Break	15	%	ISO 527
Impact Strength (Charpy, 23°C)	55	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	40	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	8	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	4.5	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness H358/30	110	MPa	ISO 2039-1
Thermal Properties			
Vicat B50	110	°C	ISO 306
HDT / A (1,8 MPa)	93	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	6	cm ³ /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Shrinkage (lengthwise, 24h)	0.5 - 0.7	%	ISO 294-4
Shrinkage (lateral, 24h)	0.5 - 0.7	%	ISO 294-4

Technical Data Sheet



ALCOM AWL 15/1 WT1471-04LB

Physical Properties

Density	1170	kg/m ³	ISO 1183
---------	------	-------------------	----------

Flammability


Flammability (1.5 mm)	HB	class	UL 94
Flammability (3.0 mm)	HB	class	UL 94

Optical Properties

Tristimulus Value Y10 of Reflection (d=2,0mm)	94	%	DIN 5033
Tristimulus Value Y10 of Transm.,d=0.5mm	0.3	%	ISO 13468

Diagrams

Spectrum Transmission



Spectrum Reflexion

