

## Technical Data Sheet



### ALCOM AWL 15/1 WT31-956LB

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Filler/Additive System	15 % special filler
Special Features	highly reflective,opaque
Market Segment	Automotive,various
Application Area	lighting,light blocking components
Typical Applications	light guides,reflectors

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 4-8 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
<b>Mechanical Properties</b>			
Flexural Modulus	2800	MPa	ISO 178
Flexural Stress (3.5% Strain)	75	MPa	ISO 178
Tensile Modulus	2900	MPa	ISO 527
Tensile Stress at Yield	45	MPa	ISO 527
Tensile Elongation at Yield	2.5	%	ISO 527
Tensile Elongation at Break	12	%	ISO 527
Impact Strength (Charpy, 23°C)	60	kJ/m <sup>2</sup>	ISO 179/1eU
Impact Strength (Charpy, -40°C)	50	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	9	kJ/m <sup>2</sup>	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	5.5	kJ/m <sup>2</sup>	ISO 179/1eA
Ball Indentation Hardness H358/30	120	MPa	ISO 2039-1
<b>Thermal Properties</b>			
Vicat B50	110	°C	ISO 306
HDT / A (1,8 MPa)	93	°C	ISO 75-1/-2
Ball Indentation Temperature	106	°C	DIN EN 60695-10-2
<b>Rheological Properties</b>			
Melt Index (MVR)	6	cm <sup>3</sup> /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Shrinkage (24h)	0.3 - 0.6	%	ISO 294-4

Technical Data Sheet



**ALCOM AWL 15/1 WT31-956LB**

**Physical Properties**

Density	1190	kg/m <sup>3</sup>	ISO 1183
---------	------	-------------------	----------

**Optical Properties**

Tristimulus Value Y10 of Reflection (d=2,0mm)	93	%	DIN 5033
Tristimulus Value Y10 of Transm.,d=0.5mm	0.4	%	ISO 13468