

Technical Data Sheet

 **Alcolor**[®]

MOCOM

ALCOLOR ABS A WT1478-04

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Colour	white, similar to RAL 9016
Thermal Stability Colourant	300 °C max.
Light Fastness Colourant	blue woolscale 7
For use in	Acrylonitrile/Butadiene/Styrene/Copolymer
Special Features	easy flow, free from cadmium, lead and diarylide pigments, dust-free, high dispersibility, high additive content
Market Segment	various
Application Area	injection moulded parts

Dosage	3 % injection moulding dependant on wall thickness and required colour intensity dependant on application and operational area
--------	--

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 3-6 h dependant on moisture content
-----------------------	---

Storage	dry, protected from light not above 30 °C
---------	--