

## Technical Data Sheet



### ALTECH ABS FC 1000/106

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Special Features	easy flow,processing stabilised,injection moulding grade
Market Segment	various,food processing industry
Typical Applications	domestic appliances,injection moulded parts,food contact

Pre-Drying Conditions	80 °C in an air circulating dryer for 3-6 h 80 °C in a dry air (dessiccant) dryer for 2-4 h dependant on moisture content max. moisture content <0,20 %
Processing Injection Moulding	melt temperature 200-240 °C mould temperature 50-80 °C
Storage	dry, protected from light
Minimum Shelf Life	months <12

Properties	Value	Dimension	Test Norm
<b>Mechanical Properties</b>			
Flexural Modulus	2600	MPa	ISO 178
Flexural Stress (3.5% Strain)	65	MPa	ISO 178
Tensile Modulus	2500	MPa	ISO 527
Tensile Stress at Yield	44	MPa	ISO 527
Tensile Elongation at Yield	2.2	%	ISO 527
Tensile Elongation at Break	8.5	%	ISO 527
Impact Strength (Charpy, 23°C)	47	kJ/m <sup>2</sup>	ISO 179/1eU
Impact Strength (Charpy, -40°C)	40	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	8	kJ/m <sup>2</sup>	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	4	kJ/m <sup>2</sup>	ISO 179/1eA
Ball Indentation Hardness H358/30	101	MPa	ISO 2039-1
<b>Thermal Properties</b>			
Vicat B50	93	°C	ISO 306
HDT / A (1,8 MPa)	81	°C	ISO 75-1/-2
<b>Rheological Properties</b>			
Melt Index (MVR)	26	cm <sup>3</sup> /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
<b>Physical Properties</b>			
Density	1060	kg/m <sup>3</sup>	ISO 1183