

Technical Data Sheet



**ALTECH ABS A 1000/660**

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Special Features	injection moulding grade,also suitable for extrusion,easy release (demoulding),heat stabilised
Market Segment	Automotive,Medical / Personal Care,various
Typical Applications	kitchenware,dashboard / instrument panels,impact protection / shock absorber

Pre-Drying Conditions	80 °C in an air circulating dryer for 3-6 h 80 °C in a dry air (dessiccant) dryer for 2-4 h dependant on moisture content max. moisture content <0,20 %
Processing Injection Moulding	melt temperature 200-240 °C mould temperature 50-80 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
<b>Mechanical Properties</b>			
Flexural Modulus	1950	MPa	ISO 178
Flexural Stress (3.5% Strain)	55	MPa	ISO 178
Tensile Modulus	1800	MPa	ISO 527
Tensile Stress at Yield	36	MPa	ISO 527
Tensile Elongation at Yield	3	%	ISO 527
Tensile Elongation at Break	7.5	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m <sup>2</sup>	ISO 179/1eU
Impact Strength (Charpy, -40°C)	155	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	33	kJ/m <sup>2</sup>	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	11	kJ/m <sup>2</sup>	ISO 179/1eA
Ball Indentation Hardness H358/30	73	MPa	ISO 2039-1
<b>Thermal Properties</b>			
Vicat B50	95	°C	ISO 306
HDT / A (1,8 MPa)	78	°C	ISO 75-1/-2
<b>Rheological Properties</b>			
Melt Index (MVR)	6	cm <sup>3</sup> /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Shrinkage (24h)	0.5 - 0.8	%	ISO 294-4

## Technical Data Sheet



### ALTECH ABS A 1000/660

(Last update: 17.08.2023)

#### Physical Properties

Density	1040	kg/m <sup>3</sup>	ISO 1183
---------	------	-------------------	----------

#### Flammability

Flammability (1.5 mm)	HB	class	UL 94
-----------------------	----	-------	-------