

Technical Data Sheet



ALTECH ABS A 1000/566

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Colour	black
Special Features	heat stabilised, low gloss
Market Segment	Automotive
Application Area	injection moulded parts, clothing / fasteners

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 3-6 h dependant on moisture content max. moisture content <0,20 %
Processing Injection Moulding	melt temperature 200-240 °C mould temperature 50-80 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress (3.5% Strain)	68	MPa	ISO 178
Tensile Modulus	2200	MPa	ISO 527
Tensile Stress at Yield	49	MPa	ISO 527
Tensile Elongation at Yield	3	%	ISO 527
Tensile Elongation at Break	13	%	ISO 527
Impact Strength (Charpy, 23°C)	110	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	95	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	15	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	8.5	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness H358/30	95	MPa	ISO 2039-1
Thermal Properties			
Vicat B50	105	°C	ISO 306
HDT / A (1,8 MPa)	95	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	8	cm ³ /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Shrinkage (24h)	0.4 - 0.8	%	ISO 294-4
Physical Properties			
Density	1060	kg/m ³	ISO 1183

Technical Data Sheet



ALTECH ABS A 1000/566

(Last update: 23.02.2022)

Flammability

Flammability (1.5 mm)

Glow Wire (GWFI, 650°C, 1.0mm)

Glow Wire (GWFI, 650°C, 2.0mm)

HB

passed

passed

class

-

-

UL 94

DIN EN 60695

DIN EN 60695