

## Technical Data Sheet



### ALCOLOR Function HTC UV A WT3057-09

Base Polymer	High Temperature Copolyester
Colour	white
Thermal Stability Colourant	280 °C max.
Light Fastness Colourant	blue woolscale 8
For use in	High Temperature Copolyester
Special Features	free from cadmium, lead and diarylide pigments
Typical Applications	various

---

Dosage	3,0 % extrusion 3,0 % injection moulding
Pre-Drying Conditions	90 °C in a dry air (dessiccant) dryer for 4-6 h
Processing Injection Moulding	melt temperature 260-280 °C mould temperature 40-65 °C
Storage	dry, protected from light not above 30°C