+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

## **Technical Data Sheet**

## - Alcolor®

## **M**COM

## **ALCOLOR PA A GY1047-09**

Base Polymer Polyamide 6

Colour grey

Thermal Stability Colourant 300 °C max.
Light Fastness Colourant blue woolscale 8
For use in Polyamide

Special Features free from cadmium, lead and diarylide pigments, dust-free, high additive

content, high dispersibility

Market Segment Automotive, electrical and electronic, Furniture, building and construction,

sport and leisure

Application Area injection moulded parts

Dosage 4 % injection moulding

dependant on wall thickness and required colour intensity

dependant on application and operational area

Pre-Drying Conditions 80 °C in a dry air (dessiccant) dryer

for 2-12 h

dependant on moisture content max. moisture content <0,12 %

Storage dry, protected from light

not above 30°C