

Technical Data Sheet



ALCOLOR PA A BL925-9126

Base Polymer	Polyamide 6
Colour	blue, similar to RAL 5017
Thermal Stability Colourant	280 °C max.
Light Fastness Colourant	blue woolscale 7
For use in	Polyamide
Special Features	free from cadmium, lead and diarylide pigments, dust-free, high dispersibility, high additive content
Market Segment	electrical and electronic, Furniture, building and construction, sport and leisure
Application Area	injection moulded parts, blow moulded parts, extruded parts

Dosage	extrusion 1-2 % injection moulding 1-2 % dependant on wall thickness and required colour intensity dependant on application and operational area
Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content
Processing Injection Moulding	melt temperature 250-270 °C mould temperature 40-80 °C
Storage	dry, protected from light