

Technical Data Sheet



ALTECH PA6 A 2030/212 GF30 IM UV

Base Polymer	Polyamide 6
Filler/Additive System	30 % glass fibres
Colour	grey,natural color
Special Features	heat stabilised,impact modified,UV stabilised,nucleated,processing stabilised
Market Segment	Machinery,electrical and electronic
Application Area	various,injection moulded parts,functional components

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
Processing Injection Moulding	melt temperature 270-290 °C mould temperature 80-100 °C
Storage	dry, protected from light

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	7700 / -	MPa	ISO 178
Flexural Strength	220 / -	MPa	ISO 178
Tensile Modulus	8700 / -	MPa	ISO 527
Tensile Strength at Break	140 / -	MPa	ISO 527
Tensile Elongation at Break	3.7 / -	%	ISO 527
Impact Strength (Charpy, 23°C)	85 / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	18 / -	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	210 / *	°C	ISO 75-1/-2
DSC (Melt Point)	220 / *	°C	ISO 11357
Rheological Properties			
Shrinkage (lengthwise, 24h)	0.3 - 0.5	%	ISO 294-4
Shrinkage (lateral, 24h)	0.7 - 0.9	%	ISO 294-4
Physical Properties			
Density	1330 / -	kg/m ³	ISO 1183