

Technical Data Sheet



ALTECH PA6 A 1000/677

Base Polymer	Polyamide 6
Colour	white
Special Features	fast solidifying,easy release (demoulding),heat stabilised
Market Segment	building and construction,various
Application Area	interior decoration / finishing,profiles,various,injection moulded parts
Typical Applications	window profile,various

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
-----------------------	---

Processing Injection Moulding	melt temperature 250-270 °C mould temperature 60-100 °C
-------------------------------	--

Storage	dry, protected from light
---------	---------------------------

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	3400 / -	MPa	ISO 178
Flexural Stress (3.5% Strain)	110 / -	MPa	ISO 178
Tensile Modulus	3700 / -	MPa	ISO 527
Tensile Stress at Yield	83 / -	MPa	ISO 527
Tensile Elongation at Yield	3.8 / -	%	ISO 527
Tensile Elongation at Break	17 / -	%	ISO 527
Impact Strength (Charpy, 23°C)	no break / -	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	no break / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	4 / -	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	3.5 / -	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	67 / *	°C	ISO 75-1/-2
DSC (Melt Point)	220 / *	°C	ISO 11357
Rheological Properties			
Shrinkage (lengthwise, 24h)	1 - 1.2	%	ISO 294-4
Shrinkage (lateral, 24h)	1.2 - 1.4	%	ISO 294-4
Physical Properties			
Density	1110 / -	kg/m ³	ISO 1183