

Technical Data Sheet



ALCOM PA66 910/1.1 CF10 PTFE10IM

Base Polymer	Polyamide 66
Filler/Additive System	10 % carbon fibres, 10 % PTFE
Special Features	improved sliding / wear, heat stabilised, electrically conductive, reduced surface resistivity, impact modified
Market Segment	Automotive, Machinery
Application Area	injection moulded parts
Typical Applications	functional components

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content
Processing Injection Moulding	melt temperature 280-300 °C mould temperature 80-120 °C
Storage	dry, protected from light

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	6700 / 4800	MPa	ISO 178
Flexural Strength	185 / 130	MPa	ISO 178
Tensile Modulus	8200 / 5200	MPa	ISO 527
Tensile Strength at Break	125 / 100	MPa	ISO 527
Tensile Elongation at Break	3.8 / 8.1	%	ISO 527
Impact Strength (Charpy, 23°C)	50 / 65	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	11 / 14	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	248 / *	°C	ISO 75-1/-2
DSC (Melt Point)	263 / *	°C	ISO 11357
Electrical Properties			
Surface Resistance	* / 500	Ohm	IEC 62631-3-2
Rheological Properties			
Shrinkage (lengthwise, 24h)	0.1 - 0.3	%	ISO 294-4
Shrinkage (lateral, 24h)	0.5 - 0.7	%	ISO 294-4
Physical Properties			
Density	1190 / -	kg/m ³	ISO 1183