

Technical Data Sheet



ALCOLOR PC A WT939-2384

Base Polymer	Polycarbonate
Colour	white
Thermal Stability Colourant	300 °C max.
Light Fastness Colourant	blue woolscale 8
For use in	Polycarbonate
Special Features	free from cadmium, lead and diarylide pigments, dust-free, high dispersibility, high additive content
Market Segment	electrical and electronic, Furniture, building and construction, sport and leisure
Application Area	injection moulded parts, blow moulded parts, extruded parts

Dosage	10 % injection moulding 10 % extrusion dependant on wall thickness and required colour intensity
--------	--

Pre-Drying Conditions	in a dry air (dessiccant) dryer 100-120 °C for 2-3 h dependant on moisture content max. moisture content <0,02 %
-----------------------	---

Storage	dry, protected from light
---------	---------------------------