+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

Technical Data Sheet

-Alcolor®

MCOM

ALCOLOR PC FC GY3054-09

Base Polymer Polycarbonate

Colour grey, similar to RAL 7032

Thermal Stability Colourant 300 °C max.
Light Fastness Colourant blue woolscale 8
For use in Polycarbonate

Special Features food contact, free from cadmium, lead and diarylide pigments, high

additive content, dust-free, high dispersibility

Market Segment electrical and electronic, Furniture, building and construction, food

processing industry, household goods

Application Area extruded parts, injection moulded parts

Dosage 3,0 % extrusion

3,0 % injection moulding

dependant on wall thickness and required colour intensity

dependant on application and operational area

Pre-Drying Conditions 120 °C in a dry air (dessiccant) dryer

for 2-3 h

120 °C in an air circulating dryer

for 4-12 h

dependant on moisture content max. moisture content <0,02 %

Storage dry, protected from light

not above 30°C