+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)

Technical Data Sheet

- Alcolor®

MCOM

ALCOLOR PC FC WT1040-11TL

Base Polymer Polycarbonate
Colour white, translucent
Thermal Stability Colourant 300 °C max.
Light Fastness Colourant blue woolscale 8
For use in Polycarbonate

Special Features free from cadmium, lead and diarylide pigments, dust-free, high

dispersibility

Market Segment Lighting, electrical and electronic
Application Area extruded parts, injection moulded parts

Dosage 3,0 % extrusion

3,0 % injection moulding

dependant on wall thickness and required colour intensity

dependant on application and operational area

Pre-Drying Conditions in a dry air (dessiccant) dryer 100-120 °C

for 2-3 h

in an air circulating dryer 100-120 °C

for 4-12 h

dependant on moisture content

Storage dry, protected from light