

Technical Data Sheet



ALCOLOR PC FC WT931-2156/3

Base Polymer	Polycarbonate
Colour	white, similar to RAL 9010, similar to RAL 9016
Thermal Stability Colourant	300 °C max.
Light Fastness Colourant	blue woolscale 8
For use in	Polycarbonate
Special Features	food contact, free from cadmium, lead and diarylide pigments, dust-free, high additive content, high dispersibility, easy flow
Market Segment	various
Application Area	injection moulded parts

Dosage	15 % injection moulding dependant on wall thickness and required colour intensity dependant on application and operational area
Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-3 h 120 °C in an air circulating dryer for 4-12 h dependant on moisture content max. moisture content <0,02 %
Storage	dry, protected from light not above 30°C