

Technical Data Sheet



ALCOLOR POM WT5015-18

Base Polymer	Polyoxymethylene/general
Colour	white, similar to RAL 9016, similar to RAL 9010
Thermal Stability Colourant	220 °C max.
Light Fastness Colourant	blue woolscale 8
For use in	Polyoxymethylene/general, Polyoxymethylene Copolymer
Special Features	free from cadmium, lead and diarylide pigments, high additive content, high dispersibility, dust-free
Market Segment	Machinery, electrical and electronic, Furniture, building and construction, sport and leisure
Application Area	extruded parts, injection moulded parts

Dosage	2,0 % extrusion 2,0 % injection moulding dependant on wall thickness and required colour intensity dependant on application and operational area
Pre-Drying Conditions	in a dry air (dessiccant) dryer 100-110 °C for 2-3 h in an air circulating dryer 100-110 °C for 3-5 h
Processing Injection Moulding	melt temperature 180-220 °C mould temperature 60-100 °C
Storage	dry, protected from light tightly sealed