

Technical Data Sheet



ALTECH PP-H ECO 2030/156 CP GF30

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	30 % glass fibres
Special Features	chemically coupled, heat stabilised, contains recycled material
Typical Applications	various, injection moulded parts

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h
Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	5300	MPa	ISO 178
Flexural Strength	100	MPa	ISO 178
Tensile Modulus	6100	MPa	ISO 527
Tensile Strength at Break	65	MPa	ISO 527
Tensile Elongation at Break	3.7	%	ISO 527
Impact Strength (Charpy, 23°C)	42	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	10	kJ/m ²	ISO 179/1eA
Thermal Properties			
HDT / A (1,8 MPa)	142	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	3.5	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.2 - 0.4	%	ISO 294-4
Shrinkage (lateral, 24h)	0.4 - 0.6	%	ISO 294-4
Physical Properties			
Density	1150	kg/m ³	ISO 1183
Ecological Properties			
Global Warming Potential (GWP)	1.06	kg CO ₂ eq./kg	ISO 14040, 14044