



**Product Data Sheet &
General Processing Conditions**

**PermaStat PLUS® 700 A
Low Density Polyethylene (LDPE)
Permanently Anti-static
ESD Protection**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.93	0.93	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0200 - 0.0400 in/in	2.00 - 4.00 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	No Break	No Break	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	1000 psi	7 MPa	D 638
Tensile Elongation	> 500.0 %	> 500.0 %	D 638
Tensile Modulus	0.03 x 10 ⁶ psi	207 MPa	D 638
Flexural Strength	1100 psi	8 MPa	D 790
Flexural Modulus	0.03 x 10 ⁶ psi	207 MPa	D 790

ELECTRICAL

Volume Resistivity	1E7 - 9.9E8 ohm.cm	1E7 - 9.9E8 ohm.cm	D 257
Surface Resistivity	1E8 - 9.9E9 ohm/sq	1E8 - 9.9E9 ohm/sq	D 257
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 0.50 s	< 0.50 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	350 - 400 °F	177 - 204 °C
Mold Temperature	70 - 120 °F	21 - 49 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C

PROCESSING NOTES

Do not exceed 520 °F (270 °C) melt temperature.