



(+) 18816996168
Ponciplastics.com

**Product Data Sheet &
General Processing Conditions**

**RTP 799 X 146802
High Density Polyethylene (HDPE)
Glass Bubbles
Preliminary Datasheet**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.71	0.71	D 792

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	11.0 ft-lbs/in	587 J/m	D 4812
Tensile Strength	800 psi	6 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.04 x 10 ⁶ psi	276 MPa	D 638
Flexural Strength	1350 psi	9 MPa	D 790
Flexural Modulus	0.06 x 10 ⁶ psi	414 MPa	D 790

THERMAL

Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	380 - 450 °F	193 - 232 °C
Mold Temperature	70 - 150 °F	21 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C