



**Product Data Sheet &
General Processing Conditions**

**VLF 80209 A
Nylon 6 (PA)
Long Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	50 %	50 %	
Specific Gravity	1.56	1.56	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0030 in/in	0.10 - 0.30 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	6.0 ft-lbs/in	320 J/m	D 256
unnotched 1/8 in (3.2 mm) section	25.0 ft-lbs/in	1335 J/m	D 4812
Tensile Strength	33000 psi	228 MPa	D 638
Tensile Elongation	2.0 - 3.0 %	2.0 - 3.0 %	D 638
Tensile Modulus	2.60 x 10 ⁶ psi	17927 MPa	D 638
Flexural Strength	48000 psi	331 MPa	D 790
Flexural Modulus	2.40 x 10 ⁶ psi	16548 MPa	D 790

THERMAL

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	470 - 520 °F	243 - 271 °C
Mold Temperature	130 - 200 °F	54 - 93 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.20 %	0.20 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Use a reverse barrel profile. To maximize fiber length, the following injection barrel, screw, and tip designs should be followed. L/D ratio 16/1 - 22/1, Compression ratio 2:1, Flight depth 0.200 in (5 mm) minimum, in feed section, Screw diameter 0.65 - 0.80 in (16.5 - 20 mm) minimum, Compression section length 12 - 13 diameters, Check ring valve assembly - free flow type no restrictions, Nozzle orifice 0.250 in (6 mm) diameter. Feed throat from hopper to machine must have sufficient opening to prevent bridging of long pellet composition.

Desiccant Type Dryer Required.