



**Product Data Sheet &
General Processing Conditions**

**PermaStat® 300 A
Polycarbonate (PC)
Permanently Anti-static
ESD Protection**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.19	1.19	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0060 - 0.0090 in/in	0.60 - 0.90 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	15.0 ft-lbs/in	801 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	7700 psi	53 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.27×10^6 psi	1862 MPa	D 638
Flexural Strength	12000 psi	83 MPa	D 790
Flexural Modulus	0.31×10^6 psi	2137 MPa	D 790

ELECTRICAL

Volume Resistivity	1E8 - 9.9E10 ohm.cm	1E8 - 9.9E10 ohm.cm	D 257
Surface Resistivity	1E10 - 9.9E11 ohm/sq	1E10 - 9.9E11 ohm/sq	D 257
Surface Resistance	1E9 - 9.9E10 ohm	1E9 - 9.9E10 ohm	ESD STM11.11
Static Decay	< 2.00 s	< 2.00 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	6000 - 10000 psi	41 - 69 MPa
Melt Temperature	430 - 470 °F	221 - 243 °C
Mold Temperature	150 - 250 °F	66 - 121 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Do not exceed 520 °F (270 °C) melt temperature.
Desiccant Type Dryer Required.