

(+) 18816996168

Ponciplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 4607
Syndiotactic Polystyrene (SPS)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	40 %	40 %	
Specific Gravity	1.33	1.33	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 in/in	0.20 %	D 955
Water Absorption, 24 hrs @ 23°C	0.010 %	0.010 %	D 570

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	2.2 ft-lbs/in	117 J/m	D 256
unnotched 1/8 in (3.2 mm) section	10.0 ft-lbs/in	534 J/m	D 4812
Tensile Strength	19500 psi	134 MPa	D 638
Tensile Elongation	1.4 %	1.4 %	D 638
Tensile Modulus	1.70 x 10 ⁶ psi	11722 MPa	D 638
Flexural Strength	27000 psi	186 MPa	D 790
Flexural Modulus	1.70 x 10 ⁶ psi	11722 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	460 °F	238 °C	D 648
--	--------	--------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	560 - 620 °F	293 - 327 °C
Mold Temperature	160 - 300 °F	71 - 149 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C