

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 1503-55D
Polyether-Ester Block Copolymer
(TEEE/COPE)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.35	1.35	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0017 - 0.0025 in/in	0.17 - 0.25 %	D 955
MECHANICAL			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	6.4 ft-lbs/in	342 J/m	D 256
unnotched 1/8 in (3.2 mm) section	20.0 ft-lbs/in	1068 J/m	D 4812
Tensile Strength	6250 psi	43 MPa	D 638
Tensile Elongation	8.8 %	8.8 %	D 638
Tensile Modulus	0.33 x 10 ⁶ psi	2275 MPa	D 638
Flexural Strength	7250 psi	50 MPa	D 790
Flexural Modulus	0.24 x 10 ⁶ psi	1655 MPa	D 790
Hardness			
Shore D, instantaneous	65	65	D 2240

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Melt Temperature	430 - 480 °F	221 - 249 °C
Mold Temperature	70 - 120 °F	21 - 49 °C
Drying	2 - 3 hrs @ 212 °F	2 - 3 hrs @ 100 °C
Moisture Content	< 0.10 %	< 0.10 %

PROCESSING NOTES

Desiccant Type Dryer Required.