

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**PermaStat® 1200 T-70A
Thermoplastic Polyurethane Elastomer
(TPUR/TPU)
Permanently Anti-static
ESD Protection
Preliminary Datasheet**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.07	1.07	D 792
MECHANICAL			
Tensile Strength Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	2400 psi	17 MPa	D 412
Tensile Elongation Break, Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	> 500.0 %	> 500.0 %	D 412
Tensile Stress Die C 0.125 in, 20 in/min (3.2 mm, 500 mm/min) @ 100 %	500.0 psi 375.0 pli	3.4 MPa 65.7 N/mm	D 412 D 624
Tear Strength, Die C			
Hardness Shore A, 10 s delay	70	70	D 2240

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	7000 - 12000 psi	48 - 83 MPa
Melt Temperature	350 - 420 °F	177 - 216 °C
Mold Temperature	60 - 150 °F	16 - 66 °C
Drying	6 hrs @ 225 °F	6 hrs @ 107 °C
Moisture Content	0.03 %	0.03 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Do not exceed 520 °F (270 °C) melt temperature.

Desiccant Type Dryer Required.