

# AKROMID® PRELIMINARY

## B28 GF 15 1 grey (8857)

PA6 GF15

AKROMID® B28 GF 15 1 grey (8857) is a 15% glass fibre reinforced, heat stabilised polyamide 6 which offers medium stiffness and strength, making it the go-to material for elevated temperature applications, for example in industrial engineering or automotive industry. It also has improved flowability, which makes it easier to process. This material is colored in grey similar to NCS S 7502-B/ RAL 7012.

### Features

heat stabilised 130    easy flow

### Properties

Modulus	Strength	Impact
<b>6.200 MPa</b>	<b>110 MPa</b>	<b>30 kJ/m<sup>2</sup></b>

## Mechanical Properties

<b>Tensile modulus</b> ISO 527-2	1 mm/min   d.a.m.	<b>6200 MPa</b>
<b>Tensile stress at break</b> ISO 527-2	5 mm/min   d.a.m.	<b>110 MPa</b>
<b>Tensile strain at break</b> ISO 527-2	5 mm/min   d.a.m.	<b>2 %</b>
<b>Charpy impact strength</b> ISO 179-1/1eU	23°C   d.a.m.	<b>30 kJ/m<sup>2</sup></b>

## Thermal Properties

<b>Melting temperature</b> ISO 11357-3	DSC, 10K/min	<b>220 °C</b>
---	--------------	---------------

## Flammability

---

<b>Flammability</b> UL 94	1,6 mm Wall thickness	<b>HB Class</b>
------------------------------	-----------------------	-----------------

---

<b>Burning rate (&lt;100 mm/min)</b> FMVSS 302	> 1 mm Thickness	<b>+</b>
---	------------------	----------

---

## General Properties

---

<b>Density</b> ISO 1183	23°C	<b>1,24 g/cm<sup>3</sup></b>
----------------------------	------	------------------------------

---

<b>Molding shrinkage</b> ISO 294-4	flow	<b>0,2 - 0,4 %</b>
	transverse	<b>0,6 - 0,8 %</b>

---

## Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin liners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



<b>D</b>	Drying time	0 - 4 h
	Drying temperature ( $\tau \leq -30^{\circ}\text{C}$ )	80 °C
	Processing moisture	0,02 - 0,1 %
<b>1</b>	Feed section	60 - 80 °C
<b>2</b>	Temperature Zone 1 - Zone 4	240 - 290 °C
<b>3</b>	Nozzle temperature	260 - 300 °C
<b>4</b>	Melt temperature	270 - 290 °C
<b>5</b>	Mold temperature	80 - 100 °C
<b>→</b>	Holding pressure, spec.	300 - 800 bar
<b>←</b>	Back pressure, spec.	50 - 150 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min