

AKROMID® PRELIMINARY

B3 GF 30 8 black (8166)

PA6 GF30

AKROMID® B3 GF 30 8 black (8166) is 30% glass fiber reinforced PA6 with high rigidity and strength. The material corresponds to the European food guideline EU 10/2011 and to the American FDA 21 CFR. This grade is suitable for parts of kitchen and household appliances.

Regulatory



Properties

Modulus

10.000 MPa

Strength

175 MPa

Impact

95 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

10000 MPa

1 mm/min | conditioned

6000 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

175 MPa

5 mm/min | conditioned

110 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

3 %

5 mm/min | conditioned

5,5 %

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

95 kJ/m²

23°C | conditioned

105 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

13 kJ/m²

23°C | conditioned

18 kJ/m²

Thermal Properties

Temperature of deflection under load HDT/A

ISO 75

1,8 MPa

210 °C

Melting temperature

ISO 11357-3

DSC, 10K/min

220 °C

Flammability

Flammability

UL 94

0,8 mm Wall thickness

HB Class

General Properties

Density

ISO 1183

23°C

1,36 g/cm³

Humidity absorption

ISO 1110

70°C, 62% r.H.

2,1 - 2,3 %

Water absorption

ISO 62

23°C, saturated

6,3 - 6,9 %

Molding shrinkage

ISO 294-4

flow


0,1 - 0,3 %

transverse

0,5 - 0,7 %

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	240 - 290 °C
3	Nozzle temperature	260 - 300 °C
4	Melt temperature	270 - 290 °C
5	Mold temperature	80 - 100 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	50 - 150 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min