

# AKROMID®

## B3 GK 30 natural (2719)

PA6 GB30

AKROMID® B3 GK 30 natural (2719) is a PA 6 filled with 30% glass beads. It is characterized by a high surface quality and low tendency to warp, which makes it suitable for use in technically demanding components in mechanical engineering and in the automotive industry.

### Features

surface modified low warpage

### Properties

Modulus

4.400 MPa

Strength

70 MPa

Impact

30 kJ/m<sup>2</sup>

## Sustainability

Recycled content 30 %

## Mechanical Properties

<b>Tensile modulus</b> ISO 527-2	1 mm/min   d.a.m.	4400 MPa
	1 mm/min   conditioned	1820 MPa
<b>Tensile stress at break</b> ISO 527-2	5 mm/min   d.a.m.	70 MPa
	5 mm/min   conditioned	38 MPa
<b>Tensile strain at break</b> ISO 527-2	5 mm/min   d.a.m.	5 %
	5 mm/min   conditioned	35 %
<b>Flexural modulus</b> ISO 178	2 mm/min   d.a.m.	3140 MPa
	2 mm/min   conditioned	1570 MPa
<b>Flexural strength</b> ISO 178	2 mm/min   d.a.m.	95 MPa
	2 mm/min   conditioned	55 MPa

<b>Charpy impact strength</b> ISO 179-1/1eU	23°C   d.a.m. 23°C   conditioned	30 kJ/m <sup>2</sup> 60 kJ/m <sup>2</sup>
<b>Charpy notched impact strength</b> ISO 179-1/1eA	23°C   d.a.m. 23°C   conditioned	3 kJ/m <sup>2</sup> 5 kJ/m <sup>2</sup>
<b>Ball indentation hardness</b> ISO 2039-1	358N/30s   conditioned 961N/30s   d.a.m.	90 MPa 180 MPa

## Thermal Properties

<b>Temperature of deflection under load HDT/A</b> ISO 75	1,8 MPa	70 °C
<b>Temperature of deflection under load HDT/B</b> ISO 75	0,45 MPa	185 °C
<b>Melting temperature</b> ISO 11357-3	DSC, 10K/min	222 °C
<b>Vicat softening temperature B50</b> ISO 306	50°C/50N	205 °C

## Flammability

<b>Flammability</b> UL 94	1,6 mm Wall thickness	HB Class
<b>Burning rate (&lt;100 mm/min)</b> FMVSS 302	> 1 mm Thickness	+

## General Properties

<b>Density</b> ISO 1183	23°C	1,34 g/cm <sup>3</sup>
<b>Humidity absorption</b> ISO 1110	70°C, 62% r.H.	2,1 %
<b>Water absorption</b> ISO 62	23°C, saturated	6,5 %
<b>Molding shrinkage</b> ISO 294-4	flow transverse	0,9 % 1,0 %

---

## Electrical Properties

---

<b>Volume resistivity</b> IEC 62631-3-1	d.a.m.	<b><math>10^{15} \Omega \times \text{cm}</math></b>
--	--------	---

---

<b>Surface resistivity</b> IEC 62631-3-2	d.a.m.	<b><math>10^{13} \Omega</math></b>
---	--------	------------------------------------

---

## Rheological Properties


---

<b>MVR</b> ISO 1133	275°C/5kg	<b><math>100 \text{ cm}^3/10 \text{ min}</math></b>
------------------------	-----------	---

---

## Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



<b>D</b>	Drying time	0 - 4 h
	Drying temperature ( $\tau \leq -30^{\circ}\text{C}$ )	80 °C
	Processing moisture	0,02 - 0,1 %
<b>1</b>	Feed section	60 - 80 °C
<b>2</b>	Temperature Zone 1 - Zone 4	240 - 290 °C
<b>3</b>	Nozzle temperature	260 - 300 °C
<b>4</b>	Melt temperature	270 - 290 °C
<b>5</b>	Mold temperature	80 - 100 °C
<b>→</b>	Holding pressure, spec.	300 - 800 bar
<b>←</b>	Back pressure, spec.	50 - 150 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min