

AKROMID®

C3 GF 60 1 black (4659)

PA66 + PA6 GF60

AKROMID® C3 GF 60 1 black (4659) is a 60% glass fibre reinforced, heat stabilised polyamide 6.6/6 - Blend.

Features

heat stabilised 130

Properties

Modulus

21.300 MPa

Strength

270 MPa

Impact

96 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

21300 MPa

1 mm/min | conditioned

13200 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

270 MPa

5 mm/min | conditioned

180 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

2,3 %

5 mm/min | conditioned

4 %

Flexural modulus

ISO 178

2 mm/min | d.a.m.

22500 MPa

Flexural strength

ISO 178

2 mm/min | d.a.m.

425 MPa

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

96 kJ/m²

23°C | conditioned

103 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

19 kJ/m²

23°C | conditioned

24 kJ/m²

Thermal Properties

Temperature of deflection under load HDT/B ISO 75	0,45 MPa	255 °C
Temperature of deflection under load HDT/C ISO 75	8 MPa	212 °C
Melting temperature ISO 11357-3	DSC, 10K/min	260 °C
Temperature index for 50% loss of tensile strength IEC 60216	5.000 h 20.000 h	160 - 175 °C 130 - 150 °C

Flammability

Flammability UL 94	1,6 mm Wall thickness	HB Class
Burning rate (<100 mm/min) FMVSS 302	> 1 mm Thickness	+

General Properties

Density ISO 1183	23°C	1,71 g/cm³
Humidity absorption ISO 1110	70°C, 62% r.H.	1,1 %
Molding shrinkage ISO 294-4	flow transverse	0,4 % 0,8 %

Electrical Properties

Volume resistivity IEC 62631-3-1	d.a.m. conditioned	10¹³ Ω x cm 10¹⁰ Ω x cm
Surface resistivity IEC 62631-3-2	d.a.m. conditioned	10¹² Ω 10¹⁰ Ω
Comparative tracking index IEC 60112	Test liquid A	600 V

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	260 - 300 °C
3	Nozzle temperature	270 - 300 °C
4	Melt temperature	270 - 300 °C
5	Mold temperature	80 - 100 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	50 - 150 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min