

AKROMID®

C3 GF 30 5 XTC black (4686)

PA66+PA6 GF30

AKROMID® C3 GF 30 5 XTC black (4686) is a 30% glass fiber reinforced, high heat stabilised polyamide 6.6/6 blend. It is characterised by high stiffness and strength as well as by excellent temperature resistance. It is therefore perfectly suitable for parts in industrial engineering and in the automotive industry, which are exposed to high temperatures.

Features

heat stabilised 230

Properties

Modulus

9.500 MPa

Strength

185 MPa

Impact

95 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

9500 MPa

1 mm/min | conditioned

5500 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

185 MPa

5 mm/min | conditioned

110 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

3,5 %

5 mm/min | conditioned

6,0 %

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

95 kJ/m²

23°C | conditioned

90 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

14 kJ/m²

23°C | conditioned

23 kJ/m²

Thermal Properties

Temperature of deflection under load HDT/A

ISO 75

1,8 MPa

220 °C

Temperature of deflection under load HDT/B ISO 75	0,45 MPa	245 °C
Melting temperature ISO 11357-3	DSC, 10K/min	245 °C
Temperature index for 50% loss of tensile strength IEC 60216	5.000 h	210 - 230 °C

Flammability

Flammability UL 94	1,6 mm Wall thickness	HB Class
Burning rate (<100 mm/min) FMVSS 302	> 1 mm Thickness	+

General Properties

Density ISO 1183	23°C	1,36 g/cm³
Humidity absorption ISO 1110	70°C, 62% r.H.	1,5 - 1,7 %
Molding shrinkage ISO 294-4	flow	0,1 - 0,3 %
	transverse	0,6 - 0,8 %

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	260 - 300 °C
3	Nozzle temperature	270 - 300 °C
4	Melt temperature	270 - 300 °C
5	Mold temperature	80 - 100 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	50 - 150 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min

Diagrams

