

AKROMID®

C3 GF 30 1 FR grey (8995)

PA66+PA6 GF30 FR(40)

AKROMID® C3 GF 30 1 FR grey (8995) is a 30 % glass fiber reinforced, flame retardant and heat stabilised PA6/6.6 blend, colored in grey similar to RAL 7012. This material is listed in all colors according to UL 94 including excellent RTI values. It is based on a flame retardant system that is free of red phosphorus, PFAS, zinc borate, halogens and melamine. This grade is also suitable for E&E applications (e.g. control cabinets) as well as for railroad applications and meets the requirements for public transportation (EN 45545-2 R22/23/24/26 HL3). Laser markable.

Features

heat stabilised 130 flame retardant laser markable
surface modified easy flow E&E public transportation

Regulatory

EN45545-2



Properties

Modulus

10.600 MPa

Strength

150 MPa

Impact

70 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

10600 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

150 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

3,0 %

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

70 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

11 kJ/m²

Thermal Properties

RTI electrical UL 746B	UL 0,4mm Wall thickness	140 °C
	UL 0,8mm Wall thickness	150 °C
	UL 1,6mm Wall thickness	150 °C
	UL 3,2mm Wall thickness	150 °C
RTI impact UL 746B	UL 0,4mm Wall thickness	120 °C
	UL 0,8mm Wall thickness	125 °C
	UL 1,6mm Wall thickness	125 °C
	UL 3,2mm Wall thickness	125 °C
RTI strength UL 746B	UL 0,4mm Wall thickness	135 °C
	UL 0,8mm Wall thickness	140 °C
	UL 1,6mm Wall thickness	140 °C
	UL 3,2mm Wall thickness	140 °C
Melting temperature ISO 11357-3	DSC, 10K/min	262 °C

Flammability

Flammability UL 94	UL 0,4 mm Wall thickness	V-0 Class
	UL 0,8 mm Wall thickness	V-0 Class
	UL 1,6 mm Wall thickness	V-0 Class
	UL 3,2 mm Wall thickness	V-0 Class
GWFI IEC 60695-2-12	UL 0,4 mm Wall thickness	960 °C
	UL 0,8 mm Wall thickness	960 °C
	UL 1,6 mm Wall thickness	960 °C
	UL 3,2 mm Wall thickness	960 °C
GWIT IEC 60695-2-13	UL 0,4 mm Wall thickness	725 °C
	UL 0,8 mm Wall thickness	725 °C
	UL 1,6 mm Wall thickness	725 °C
	UL 3,2 mm Wall thickness	725 °C
HWI UL 746A	UL 0,4 mm Wall thickness	0 PLC
	UL 0,8 mm Wall thickness	0 PLC
	UL 1,6 mm Wall thickness	0 PLC
	UL 3,2 mm Wall thickness	0 PLC
HAI UL 746A	UL 0,4 mm Wall thickness	0 PLC
	UL 0,8 mm Wall thickness	0 PLC
	UL 1,6 mm Wall thickness	0 PLC
	UL 3,2 mm Wall thickness	0 PLC

Burning rate (<100 mm/min)	> 1 mm Thickness	+
FMVSS 302		

General Properties


Density	23°C	1,41 g/cm ³
ISO 1183		
Humidity absorption	70°C, 62% r.H.	1,6 - 1,8 %
ISO 1110		
Molding shrinkage	flow	0,1 - 0,3 %
ISO 294-4	transverse	0,6 - 0,8 %

Electrical Properties

Volume resistivity	UL d.a.m.	10 ¹² Ω x cm
IEC 62631-3-1		
Comparative tracking index	Test liquid A	600 V
IEC 60112		
Comparative tracking index	UL	0 PLC
ASTM D3638		
Inclined-Plane Tracking, IPT	UL	1 kV
ASTM D2303-13		
High voltage arc tracking rate (HVTR)	UL	1 PLC
UL 746A		
High Volt, Low Current Arc Resistance	UL	6 PLC
ASTM D495		

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	2 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,08 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	260 - 290 °C
3	Nozzle temperature	260 - 300 °C
4	Melt temperature	270 - 290 °C
5	Mold temperature	60 - 100 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	30 - 100 bar
	Injection speed	medium
	Screw speed	5 - 10 m/min