

PRECITE®

P3 GF 20 black (7609)

PBT GF20

PRECITE® P3 GF 20 black (7609) is a 20% glass fiber reinforced PBT with excellent dimensional stability. Thanks to its low moisture absorption, PRECITE® achieves consistent mechanical and electrical properties, even under changing climatic conditions. With its exceptional combination of high stiffness and elongation, as well as excellent chemical resistance, the compound is ideally suited for precision engineering components in the automotive industry, mechanical engineering, electrical and electronic applications, and household goods. This grade has a higher CTI (350 V).

Features

E&E

Properties

Modulus

7.000 MPa

Strength

120 MPa

Impact

50 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

7000 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

120 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

3,5 %

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

50 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

10 kJ/m²

Thermal Properties

Temperature of deflection under load HDT/A

ISO 75

1,8 MPa

205 °C

Melting temperature

ISO 11357-3

DSC, 10K/min

225 °C

Flammability

Flammability

UL 94

1,6 mm Wall thickness

HB Class

General Properties

Density

ISO 1183

23°C

1,45 g/cm³

Molding shrinkage

ISO 294-4

flow

0,4 - 0,6 %

transverse

0,9 - 1,1 %

Electrical Properties

Comparative tracking index

IEC 60112

Test liquid A

350 V

Rheological Properties

MVR


ISO 1133

250°C/2,16kg

10 cm³/10 min

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	3 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	100 - 120 $^{\circ}\text{C}$
	Processing moisture	0,02 - 0,04 %
1	Feed section	60 - 80 $^{\circ}\text{C}$
2	Temperature Zone 1 - Zone 4	250 - 275 $^{\circ}\text{C}$
3	Nozzle temperature	250 - 280 $^{\circ}\text{C}$
4	Melt temperature	260 - 275 $^{\circ}\text{C}$
5	Mold temperature	80 - 100 $^{\circ}\text{C}$
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	30 - 100 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min