

AKROTEK®

PK-VM black (4973)

PK

AKROTEK® PK-VM black (4973) is an unreinforced Polyketone with high flowability. The outstanding friction and wear properties enable the use for demanding components exposed to tribological stress. PK is characterized by its outstanding media resistance, which qualifies it to be used for components that are in contact with chemicals. The most important markets for AKROTEK® PK are the automotive and furniture industry and mechanical engineering.

Features

hydrolysis / chemically stabilised

Properties

Modulus

1.500 MPa

Strength

60 MPa

Impact

180 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

1500 MPa

1 mm/min | conditioned

1500 MPa

Tensile stress at yield

ISO 527-2

50 mm/min | d.a.m.

60 MPa

50 mm/min | conditioned

60 MPa

Tensile strain at break

ISO 527-2

50 mm/min | d.a.m.

> 100 %

50 mm/min | conditioned

> 100 %

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

no break

23°C | conditioned

no break

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

10 kJ/m²

23°C | conditioned

10 kJ/m²

Thermal Properties

Temperature of deflection under load HDT/A

ISO 75

1,8 MPa

100 °C

Melting temperature

ISO 11357-3

DSC, 10K/min

220 °C

Flammability

Flammability

UL 94

1,6 mm Wall thickness

HB Class

General Properties

Density

ISO 1183

23°C

1,24 g/cm³

Humidity absorption

ISO 1110

70°C, 62% r.H.

0,8 - 0,9 %

Water absorption

ISO 62

23°C, saturated

2,0 - 2,4 %

Molding shrinkage

ISO 294-4

flow

1,4 - 1,6 %

transverse

1,5 - 1,7 %

Electrical Properties

Surface resistivity

IEC 62631-3-2

d.a.m.

10¹³ Ω

conditioned

10¹⁰ Ω

Rheological Properties

MVR

ISO 1133

240°C/2,16kg

60 cm³/10 min

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



| | | |
|----------|--|----------------|
| D | Drying time | 0 - 4 h |
| | Drying temperature ($\tau \leq -30^{\circ}\text{C}$) | 80 °C |
| | Processing moisture | 0,02 - 0,1 % |
| 1 | Feed section | 60 - 80 °C |
| 2 | Temperature Zone 1 - Zone 4 | 220 - 250 °C |
| 3 | Nozzle temperature | 230 - 250 °C |
| 4 | Melt temperature | 230 - 250 °C |
| 5 | Mold temperature | 60 - 120 °C |
| → | Holding pressure, spec. | 300 - 800 bar |
| ← | Back pressure, spec. | 30 - 70 bar |
| | Injection speed | medium to high |
| | Screw speed | 8 - 15 m/min |

Diagrams

