

AKROTEK® PRELIMINARY

PK-VM GF 10 FR orange (8745)

PK GF10 FR(40)

AKROTEK® PK-VM GF 10 FR orange (8745) is a 10% glass fibre reinforced, flame retardant and process improved Polyketone compound, colored in orange similar to RAL 2003. The flame retardant system is free of red phosphorous and halogens. Due to its good chemical resistance, good dimensional stability and high elongation at break it is suitable for high voltage components in e-mobility.

Features

hydrolysis / chemically stabilised flame retardant process improved E-Mobility

Properties

Modulus

4.000 MPa

Strength

70 MPa

Impact

48 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

4000 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

70 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

5,5 %

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

48 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

8 kJ/m²

Thermal Properties

Melting temperature

ISO 11357-3

DSC, 10K/min

220 °C

Flammability

Flammability	0,8 mm Wall thickness	V-0 Class
UL 94	1,6 mm Wall thickness	V-0 Class
	3,2 mm Wall thickness	V-0 Class
GWFI	0,8 mm Wall thickness	960 °C
IEC 60695-2-12	1,6 mm Wall thickness	960 °C
	3,2 mm Wall thickness	960 °C
GWIT	0,8 mm Wall thickness	825 °C
IEC 60695-2-13	1,6 mm Wall thickness	850 °C
Burning rate (<100 mm/min)	> 1 mm Thickness	+
FMVSS 302		

General Properties

Density	23°C	1,34 g/cm³
ISO 1183		
Humidity absorption	70°C, 62% r.H.	0,5 - 0,7 %
ISO 1110		
Molding shrinkage	flow	0,5 - 0,7 %
ISO 294-4	transverse	1,1 - 1,3 %

Electrical Properties

Comparative tracking index	Test liquid A	600 V
IEC 60112		

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	210 - 240 °C
3	Nozzle temperature	230 - 240 °C
4	Melt temperature	230 - 240 °C
5	Mold temperature	60 - 100 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	30 - 50 bar
	Injection speed	medium
	Screw speed	5 - 10 m/min