

AKROMID® PRELIMINARY

T5 GF 40 6 black (8002)

PPA GF40

AKROMID® T5 GF 40 6 black (8002) is a 40% glass fibre reinforced, inargonic high heat stabilised polyphthalamide. It is characterised by its good surface properties and its high stiffness and strength, even at elevated temperatures up to 120°C. Due to its low moisture absorption, the mechanical properties remain nearly unchanged even in conditioned state. Not only the good creep resistance, but also the hydrolysis and chemical resistance complement the property profile and make it the material of your choice for under the hood applications and connectors with special strength requirements.

Features

heat stabilised 160 hydrolysis / chemically stabilised surface modified reduced moisture metal substitution

Properties

Modulus

16.000 MPa

Strength

245 MPa

Impact

80 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

16000 MPa

1 mm/min | conditioned

16000 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

245 MPa

5 mm/min | conditioned

230 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

2,4 %

5 mm/min | conditioned

2,4 %

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

80 kJ/m²

23°C | conditioned

80 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

11 kJ/m²

23°C | conditioned

11 kJ/m²

Thermal Properties

Temperature of deflection under load HDT/A	1,8 MPa	280 °C
ISO 75		

Melting temperature	DSC, 10K/min	325 °C
ISO 11357-3		

General Properties

Density	23°C	1,5 g/cm³
ISO 1183		

Molding shrinkage	flow	0,1 - 0,3 %
ISO 294-4	transverse	0,5 - 0,7 %

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	120 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 90 °C
2	Temperature Zone 1 - Zone 4	320 - 350 °C
3	Nozzle temperature	330 - 350 °C
4	Melt temperature	330 - 350 °C
5	Mold temperature	120 - 160 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	50 - 150 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min

Diagrams

